

**Cyberbond Europe GmbH**  
Werner-von-Siemens-Str. 2  
D – 31515 Wunstorf  
Germany  
Tel.: + 49 / 5031 / 95 66 – 0  
FAX.: + 49 / 5031 / 95 66 – 26  
E-mail: [info@cyberbond.de](mailto:info@cyberbond.de)  
[www.cyberbond.EU.com](http://www.cyberbond.EU.com)

## TECHNICAL DATA SHEET

### CYBERBOND 9050

#### Primer for Cyanoacrylate Adhesives

##### Contents :

- 15 ml brush on glass bottle
- 500 ml plastic bottle
- 5 l container

##### Selling unit:

- 30 pieces
- 1 piece
- 1 piece

##### Chemical Base:

Ethanol, Ethylacetate

##### Physical Data:

Density at 20 °C: 0,88 g/cm<sup>3</sup>

Flashpoint: -2 °C

##### Description:

The Primer Cyberbond 9050 enables you to bond unpolare materials such as e. g. Polyethylene (PE), Polypropylene (PP), Polyoxymethylene (POM) as well as modern Thermoplastic Elastomere (TPE) by means of Cyberbond Cyanoacrylate Adhesive. Cyberbond 9050 changes the surface tension. The advantages are:

- high strength bonding of materials which could not be bonded before,
- a fast and easy to use method to support bonding,
- a higher flexibility of choosing materials.

Cyberbond 9050 will be brushed on the mating parts. After evaporation application of Cyberbond Cyanoacrylate Adhesive immediately can start. The parts also can be temporarily stored for 24 h.

The data mentioned in this data sheet, particularly the recommendations for application and use of products are based on our recent knowledge and experience. Due to the fact of having so many different materials involved and conditions of applications which are out of our influence, we strongly recommend to do sufficient tests in order to guarantee that Cyberbond products are suitable for the intended process and applications. Except for wilful acts any liability based on such recommendations or any verbal advice is hereby expressly excluded.